



# Nutsert® / Finsert® GM17







English	Français	Deutsch	Italiano	Español
Aluminium alloy* (2.5 % Mg) Natural	Alliage d'aluminium* (2.5% Mg) Brut	Aluminium* (2.5 % Mg) Blank	Lega di alluminio* (2.5% Mg) Nessuna finitura	Aluminio* (2.5% Mg) Natural
* : AA 5052, DIN 1725, AlMg2.5, Werkstoff 3.3523				



∅	e (grip)		 +0.1/-0	A	B	D	J	M	P	Part No/ref
	min.	max.		max.	+0.3/-0.2	+0.3/-0.1	max.	± 0.35	max.	
M4 x 0.7	0.50	3.00	6.10	6.00	6.50	0.50	8.10	10.75	6.80	OGM17-00430
M5 x 0.8	0.50	3.00	7.10	7.00	7.50	0.50	9.60	12.00	8.30	OGM17-00530
M6 x 1.0	0.50	3.00	9.10	9.00	9.50	0.50	12.10	14.50	10.00	OGM17-00630
M8 x 1.25	0.50	3.00	11.10	11.00	11.50	0.50	14.50	16.00	11.50	OGM17-00830

all dimensions in mm / en millimètres / alle Maße in mm / in millimetri / en milímetros

∅				
	Recommended max torque	Pull-out	Torque-to-turn	Push-out
	Nm max.	kN	Nm min.	kN
M4 x 0.7	4.0	3.7	1.6	0.7
M5 x 0.8	5.3	5.4	2.1	0.8
M6 x 1.0	10.8	8.5	2.4	0.9
M8 x 1.25	23.0	13.1	5.4	1.0



An Acument™ Global Technologies Company

www.avdel-global.com

© 2007 Acument Intellectual Properties, LLC

Nutsert® and Finsert® are trademarks of Avdel UK Limited

03.2007

Data shown is subject to change without prior notice as a result of continuous product development and improvement policy.  
Your local Avdel representative is at your disposal should you need to confirm latest information.